

tapetex wall materials

SPECIFICATION	RONDO 67-1760/-1764, a multi-layer quality
Collection	5 colors from Tapatex 67-Nonwoven
Physical Properties	
Composition	60% FSC certified woodpulp reinforced with 40% polyester.
Backing	Paper backing of 70% FSC certified woodpulp reinforced with 30%
	polyester.
Width	137 cm = 54"
Weight	Approx. 470 gr/lm = 15.2 oz/lyd
Thickness	Approx. 0.70 mm
Hanging	On repeat, H8.0 cm - 3.1" W4.0 cm - 1.6"
	Use a rubber roller instead of a spatula.
	Precision trimmed for butt-joining by professional paper hangers.
	Installation advice supplied with every roll.
Adhesive	Adhesive Tapatex PRO-1 or similar premixed, heavy duty, clear vinyl
	adhesive, suitable for textile wallcovering
Variation	There can be a variation between sample material and finished product.
	Stock cuttings are available for approval.
<b>Performance</b>	See detailed results on our website.
Surface Finish	A stain repellent finish prevents waterbased splashes penetrating and
	staining the material.
	Periodic vacuuming is recommended to prevent dust from building up on
	the material surface.
Lightfastness	Test result as per ISO 105-B02:2014, Heraeus original Hanau Xenotest
LRV Values	Testing as per BS 8493:2008+A1:2010, Datacolor DC500
Fire Rating	ASTM E84 Class 1 or A and EUROCLASS (B s1 d0)
, ,	
Indoor Air Quality	
Deach SV/UC	6
Permeability Rating Indoor Air Quality Reach SVHC DoP #	Test result 35.0 as per ASTM E96-12, Method B, Water Vapor Transmission. ASTM D6196, D5197 and D5116, Environmental Chamber Test. The test followed UL 2821 "Greengaurd Certification Program Method for Measuring and Evaluating Chemical Emissions" Compliant as per Centexbel testing. (CPR 305/2011), DOP-CPR-01

## **Sustainability**

The nonwoven is FSC certified, FSC A000531.

In production, all energy sources are either green, wind or hydro based and all processes are waterbased. The products do not contain PVC, chlorine, plasticizers, heavy metals or harmful dyes.

## Supply and Packing

Delivery from stock by the full linear meter or full linear yard. The average piece length of this quality is approx. 50 linear meters or 55 linear yards. However, as is common within the textile industry, it is not possible to establish a standard roll length. The wallcovering is reeled on to a cardboard core, wrapped in polyethylene and protective end caps are fixed. Each roll is then packed in individual cardboard boxes or tubes, which are also made out of FSC certified wood pulp.

## Harmonized System as per the World Customs Organization and Origin

Textile Wallcovering, paper backed: 5905.00. Made in the Netherlands